




### JR15K 材料特性 JR15K Material Characteristics



#### 材料特点

高磁导率 (约15000)  
high initial permeability (about 15000)

特性 Characteristics	单位	JR15K
初始磁导率 $\mu_i$ Initial Permeability		15000 $\pm$ 25%
饱和磁通密度 $B_s$ (25°C 1194A/m) Saturation magnetic density	mT	360
剩磁 $B_r$ Remanence	mT	110
矫顽力 Coercivity	A/m	4.4
相对损耗因子 $\text{tg}\delta/\mu$ iRelative loss factor	$\times 10^{-6}$	$\leq 100$ (100KHz)
电阻率 $\rho$ Electrical resistivity	$\Omega \cdot \text{m}$	0.15
居里温度 $T_c$ Curie temperature	$^{\circ}\text{C}$	$> 110$
密度 $d$ Density	$\text{kg}/\text{m}^3$	$4.95 \times 10^3$